

# Ghesquiere Plastic Testing, Inc.

DEC - 9 2002

20450 HARPER AVENUE  
HARPER WOODS, MI 48225  
PHONE (313) 885-3535  
FAX (313) 885-1771

Report Date: November 25, 2002  
Test Date: October 24-November 25, 2002

Report #0210-60381-1  
Performed for:  
Mecho Shade Systems, Inc.  
42-03 35th Street  
Long Island City, NY 11101

Attention: Mr. John Maloney

WORK REQUESTED:

Perform Fungus Resistance test on sample submitted.

DESCRIPTION OF SAMPLE:

Sample submitted was identified as PVC Coated Polyester Fabric.  
(P. O. #T8008546).

WORK PERFORMED:

Test specimens were prepared as necessary and conditioned for a minimum of 24 hours at standard laboratory conditions prior to testing.

Fungus Resistance, Mixed Culture Method was performed for 28 days at 28°C to 31°C in accordance with the procedures of ASTM G21-96.


RESULTS:

The following determinations were made based upon the above test:

FUNGUS RESISTANCE

Specimen 1	Rating 0.	No fungal growth.
Specimen 2	Rating 0.	No fungal growth.
Specimen 3	Rating 0.	No fungal growth.

Ghesquiere Plastic Testing, Inc.

  
M. W. Ghesquiere  
President

MWG/as